SANHO CHEMICAL CO., LTD.
NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
TEL：886-7-6962211~3 http：// www.sanho.com.tw
FAX：886-7-6976993 (Sales) E-mail：sanho@sanho.com.tw
FAX：886-7-6961782 (Export) E-mail：sanho@so-net.net.tw

TOHMIDE 225-XX

TOHMIDE 225-XX is a polyaminoamide type epoxy curing agent. It's major applications include general adhesives, sealants, civil engineering, concrete repair compounds and surface coatings.

1. SPECIFICATIONS

Appearance	：Brown-colored viscous liquid.
Viscosity (40℃)	：8,000~12,000 mPa·s
Colour (Gardner)	：10 Max.
Amine Value	：365±15
A.H.E.W.	：120
Sp.Gr. (25℃)	：0.97

2. RECOMMENTED MIXING RATIO

(1) 60~75 parts to 100 parts of Bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.

3. CURING CHARACTERISTICS

Epoxy resin	：Employed Bisphenol-A type epoxy resin whose epoxy equivalent weight is about 190.
Total mass	：100 gram
Room temp.	：23℃

EXOTHERMIC REACTION			
Epoxy resin / TOHMIDE 225-XX		60 / 40	
Peak exothermic time. (min.)		210	
Peak exothermic temp. (℃)		35	