



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
 TEL : 886-7-6962211~3 http : // www.sanho.com.tw
 FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
 FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

4. CURING PROPERTIES

A-Component

NPEL-128.....100

B-Component

KINGCURE X-963.....30

Gel Time	(20°C ,100gm)	11.5 min
Pot Life	(20°C ,200 km)	8 min.
Dry Touch	(20°C ,200 km)	80 min.
Curing	(20°C ,200 km)	130 min.
Curing	(5°C ,200 km)	25hr.

5. SUGGESTRD FORMULATIONS

(1) Epoxy Mortar

A-Component

NPEL-128.....100

Benzyl Alcohol.....15

B-Component

KINGCURE X-963.....30

A-Component

NPEL-128.....100

B-Component

KINGCURE X-963.....15

Jeffmine D-230.....15

(2) Under-water Coating

A-Component

NPEL-114.....100

B-Component

KINGCURE X-963.....30

Nonyl Phenol.....7