



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
TEL : 886-7-6962211~3 http : // www.sanho.com.tw
FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

KINGCURE 100-BD

KINGCURE 100-BD is a modified aliphatic polyamines epoxy curing agent. Fast setting adhesives , cold weather patching compounds , It has been designed for use in solvent-less coatings and leveling floorings where excellent flow, good adhesion and high gloss films are required.

1. SPECIFICATIONS

Appearance	: Light yellow color low viscosity liquid.
Viscosity	: 3,000~6,000mPa · s (25°C)
Color (Gardner)	: 6 Max.
Amine Value	: 790±30
A.H.E.W.	: 45

2. RECOMMENDED MIXING RATIO

20~35 parts by weight to 100 parts of bisphenol-A type liquid epoxy resin whose epoxy equivalent weight is about 190.

3. CURING CHARACTERISTICS

3-1 Exothermic Reaction.

Epoxy resin	: bisphenol-A type liquid epoxy resin whose epoxy equivalent weight is about 190.
Total mass	: 100g
Room temperature	: 23°C

Epoxy resin / KINGCURE 100-BD	80/20
Peak exothermic time. (min.)	12
Peak exothermic temp. (°C)	218
Gel time (min.)	8

(Use PE Cup)