





# SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.  
TEL : 886-7-6962211~3      http : // www.sanho.com.tw  
FAX : 886-7-6976993 (Sales)      E-mail : sanho@sanho.com.tw  
FAX : 886-7-6961782 (Export)      E-mail : sanho@so-net.net.tw

Mixing Ratio : Epoxy varnish / TOHMIDE 437	100 / 45	100 / 36
Cross Cut (1 mm width)	100/100	100/100
Bending test (2 mm  )	No abnormality	No abnormality
Erichsen value (6 mm)	No abnormality	No abnormality
Impact resistance (Face)	No abnormality	No abnormality
( Falling-Ball method 1/2" dia, 500gram, 500cm height) (Back)	No abnormality	No abnormality
CHEMICAL RESISTANCE (one month)		
Tap Water	No abnormality	No abnormality
5% solution of salt water	No abnormality	No abnormality
10% solution of caustic soda	No abnormality	No abnormality
5% solution of sulfuric acid	9S	9S
Salt spray ( 72 hours ,Swelling distance from the cut point of film)	3 ~ 4 mm	2 mm