



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

3. LAP SHEAR STRENGTH

EPOXY RESIN / KINGCURE K-863A	100 / 20	100 / 30	100 / 40
LAP SHEAR STRENGTH (KGF/CM ²)	123	127	128

4. CHEMICAL RESISTANCE

EPOXY RESIN / K-863A	100 / 20			100 / 30			100 / 40		
	1	7	30	1	7	30	1	7	30
TAP WATER (23°C)	0.1	0.3	0.7	0.1	0.4	1.0	0.1	0.5	1.1
5% SALT SOLUTION	0.1	0.3	0.8	0.1	0.4	0.9	0.1	0.5	1.2
10% CAUSTIC SODA SOLUTION	0.1	0.4	0.6	0.1	0.4	0.8	0.1	0.4	1.0
10% AMMONIA SOLUTION	0.1	0.3	0.7	0.1	0.4	0.9	0.2	0.5	1.1
5% SULFURIC ACID SOLUTION	0.1	0.4	0.8	0.3	0.7	1.3	0.8	1.7	3.3
5% HYDROCHLORIC ACID SOLUTION	0.2	0.4	0.8	0.2	0.6	1.1	0.5	1.1	2.2
KEROSENE	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ISOPROPANOL	0.0	0.0	0.0	0.0	0.0	0.0	0.0	-0.1	0.0
METHYL-ISOBUTYL-KETONE	4.6	8.7	9.8	0.2	0.6	1.3	0.1	0.1	0.2