



# **SANHO CHEMICAL CO., LTD.**

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.  
TEL : 886-7-6962211~3      [http : // www.sanho.com.tw](http://www.sanho.com.tw)  
FAX : 886-7-6976993 (Sales)      E-mail : sanho@sanho.com.tw  
FAX : 886-7-6961782 (Export)      E-mail : sanho@so-net.net.tw

## **FUJICURE 4030**

FUJICURE 4030 is a solvent type epoxy curing agent of modified aromatic polyamine, designed for such coating applications as tar-epoxy system and enamel type. It provides high performance epoxy paint for low temperature and wet surface ,it is cured film with high orders of curing properties, and superior anti-chemical resistance,water resistance

### **1. SPECIFICATIONG**

Appearance	: Brown, viscous liquid
Solid content (%)	: $68 \pm 2$
Viscosity (Gardner Holdt/25°C)	: Z~ Z <sub>3</sub>
Amine value (JIS)	: $200 \pm 10$
Color (Gardner)	: 7 Max.
A.H.E.W.	: 160
Solvent (ratio)	: Xylene /Isobutanol = 70/30

### **2. RECOMMENDED MIXING RATIO**

- (1). 70 ~ 100 parts by weight to 100 parts of liquid epoxy resin whose epoxy equivalent weight is about 190.
- (2) 25 ~ 45 parts by weight to 100 parts of liquid epoxy resin whose epoxy equivalent weight is about 490.