



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.

TEL : 886-7-6962211~3

[http : // www.sanho.com.tw](http://www.sanho.com.tw)

FAX : 886-7-6976993 (Sales)

E-mail : sanho@sanho.com.tw

FAX : 886-7-6961782 (Export)

E-mail : sanho@so-net.net.tw

TOHMIDE 215-70X

TOHMIDE 215-70X curing agent is a reactive polyamide intended for use in curing of epoxy resin . TOHMIDE 215-70X is cut to 70 %solids by weight in Xylene ,When cured with ac high molecule weight of epoxy resin .it is provides cured films with such high orders desired at actual application field as good flexibility, simultaneously with good water resistance and good alkali resistance.

1. SPECIFICATIONS

Appearance	: Brown, viscous liquid
Solid content (%)	: 70 ± 2
Viscosity (Gardner Holdt/25°C)	: T~ X
Amine value (JIS)	: 170 ± 10
Color (Gardner)	: 9 Max.
A.H.E.W.	: 240
Solvent (ratio)	: Xylene 100%

2. RECOMMENDED MIXING RATIO

40~60 parts by weight to 100 parts of epoxy resin whose epoxy equivalent weight is about 490.