



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

FUJICURE 5003-D

FUJICURE 5003-D is a modified cycloaliphatic amine. The curing of FUJICURE 5003-D is excellent under high humid conditions or on the surface of the damp. The primary application of FUJICURE 5003-D is for coatings, linings, and castings.

1. SPECIFICATIONS

Appearance	: Light yellow color, viscous liquid.
Viscosity (mPa · s /25°C)	: 1,000 ~ 2,000
Amine Value (JIS)	: 325 ± 15
Color (Gardner)	: 5 Max .
Specific Gravity (25 / 25°C)	: 1.10
Flash Point	: 187°C
A.H.E.W.	: 120

2. RECOMMENDED MIXING RATIO

50~70parts by weight to 100 parts of bisphenol-A liquid whose epoxy equivalent weight is about 190.

3. CURING CHARACTERISTICS

3-1 Exothermic Reaction.

Epoxy resin	: bisphenol-A type liquid whose epoxy equivalent weight is about 190.
Total mass	: 100g
Room temperature	: 23°C

Epoxy resin / FUJICURE 5003-D	100 / 53	100 / 66	100 / 81
Peak exothermic time. (min.)	104	94	83
Peak exothermic temp. (°C)	121	137	144
Gel time (min.)	82	76	68



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
 TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
 FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
 FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

3-2 Drying Characteristics

Epoxy resin : bisphenol-A type liquid whose epoxy equivalent weight is about 190.

By RCI Drying Recorder : At 23°C and 5°C

Epoxy resin / F-5003-D		100 / 53	100 / 66	100 / 66
23°C	Set to touch (hours)	4.0	3.5	3.1
	Tack free (hours)	8.2	7.0	6.7
	Dry through (hours)	12.2	8.9	7.4
5°C	Set to touch (hours)	2.4	2.4	3.9
	Tack free (hours)	25.8	23.7	23.4
	Dry through (hours)	35.1	34.8	34.8

©Film thickness about 150um

4. MECHANICAL PROPERTIES

Epoxy resin : bisphenol-A type liquid whose epoxy equivalent weight is about 190.

Precured at 23°C for one day After this cured at 80°C for 2 hours.

Epoxy resin / F-5003-D		100 / 53	100 / 66	100 / 81
Tensile Strength	(kgf/mm ²)	5.7	5.0	5.4
Bending Strength	(kgf/mm ²)	7.7	8.2	7.5
Flexural Modulus	(kgf/mm ²)	260	280	250
Compressive strength	(kgf/mm ²)	7.3	7.3	6.4
Izod Impact Strength	(kgf/cm-cm)	1.5	2.2	2.3
Rockwell Hardness	(m-scale)	28	30	26
. Heat Distortion	(°C)	42	45	40
Shore D		80	80	78

5. CHEMICAL RESISTANCE

Epoxy resin : bisphenol-A type liquid whose epoxy equivalent weight is about 190

Precured at 23°C for one day After this cured at 80°C for 2 hours

Measured the weight change of the cured products after immersing them into following chemical substrates



SANHO CHEMICAL CO., LTD.

NO. 1, ZHONGSHAN S. RD., LUZHU DIST., KAOHSIUNG CITY, TAIWAN.
TEL : 886-7-6962211~3 [http : // www.sanho.com.tw](http://www.sanho.com.tw)
FAX : 886-7-6976993 (Sales) E-mail : sanho@sanho.com.tw
FAX : 886-7-6961782 (Export) E-mail : sanho@so-net.net.tw

Unit : %

Epoxy Resin / F-5003-D	100 / 53			100 / 66			100 / 81		
	1	7	30	1	7	30	1	7	30
Tap water	0.2	0.5	1.6	0.2	0.4	1.0	0.2	0.5	1.2
5% salt water solution	0.2	0.5	1.2	0.2	0.5	1.2	0.2	0.5	1.3
10% caustic soda solution	0.1	0.4	1.0	0.1	0.4	1.0	0.1	0.4	1.1
10% ammonia solution	0.2	0.6	1.3	0.2	0.6	1.5	0.2	0.6	1.5
5% sulfuric acid solution	0.3	0.7	1.6	0.5	1.2	2.5	1.0	2.4	5.2
5% hydrochloric acid solution	0.2	0.6	1.4	0.3	0.9	1.8	0.5	1.3	3.0
Kerosene	0.1	0.1	0.3	0.1	0.1	0.3	0.1	0.3	0.7
Isopropanol	1.1	3.1	4.0	1.1	3.4	6.4	1.5	4.9	11
Methyl isobutyl ketone	15	broken	broken	5.8	broken	broken	8.1	broken	broken

6. HANDLING (SAFETY) PRECAUTIONS

Since FUJICURE 5003-D is a modified-amine curing agent, it should be handled with normal care.

Avoid direct contact with any parts of human body. in the case of eye or skin contamination with FUJICURE 5003-D, the affected part must be first washed thoroughly with plenty of water and soap.

In the case of eye contact, consult a physician afterwards. Keep the container tightly. Seal and store in a cool and dry place away from open flames.

7. IMPORTANT NOTICE

All statement technical information, data and recommendations contained in the catalogue are based on tests we believe to be reliable but those are not to be taken as any form of our guar-antes for specific properties of our product, nor for any particular applications.

Further study of individual user is requested in the actual usage. User shall determine the suitability of the product for his intended use before using.